



**Derwent
Data** > Click
Here

Value added pa
scientific inform

[Search](#)

[Login](#)

[Register](#)

[Order Form](#)

[Shopping Cart](#)

[Premium Features](#)



**Inquire
Regarding
licensing**



P635579B1:Horseshoes of race horse made from metal alloy

[View images \(4 pages\)](#) | [View Cart](#) | [View INPADOC only](#) | [Derwent Record...](#)

Add to cart: [PDF \(~380 KB\)](#) | [TIFF](#) | [Fax](#) | [File History](#) | [More choices...](#)

EP European Patent Office (EPO)

B1 Patent

Uhm, Young ho
Nam, Tae un

KOREA RACING ASSOCIATION

News, Profiles, Stocks and More about this company

Jan. 29, 1997 / July 21, 1993

EP1993000401887

C22C 21/06; A01L 1/02; A01L 3/02;

C22C21/06; A01L1/00; A01L3/00;



Show legal status actions

DE, FR, GB

Lemoine, Robert;

Show known family members

CHEMABS 121(26)306127R CHEMABS 122(12)139964Y DERABS C94-285434

No patents reference this one

Gallery of Patents



**Alternative
Searches**



Patent Number



Boolean Text



Advanced Text

Br ws



U.S. Class
by title



U.S. Class
by number



IP Listing
Search

1 / 4 OrderPatent



Europäisches Patentamt

European Patent Office

Office européen des brevets

EP 0 635 579 B1

(11)

EUROPEAN PATENT SPECIFICATION



(19)

(12)

(45) Date of publication and mention of the grant of the patent:
29.01.1997 Bulletin 1997/05

(51) Int Cl.: C22C 21/06, A01L 1/02, A01L 3/02

(21) Application number: 83401887.0

(22) Date of filing: 21.07.1983

(54) Horseshoes of race horse made from metal alloy

Hufeisen aus Metallegerung für Rennpferde

Fers à cheval en alliage pour cheval de course

(84) Designated Contracting States:
DE FR GB

(74) Representative: Lemoine, Robert
Cabinet Malémont
42, Avenue du Président Wilson
75116 Paris (FR)

(43) Date of publication of application:
25.01.1995 Bulletin 1995/04

(56) References cited:
FR-A- 980 539
US-A- 4 655 293

(73) Proprietor: KOREA RACING ASSOCIATION
Kwachuŋ-City, Kyungki-Province (KR)

(72) Inventors:

• Uhm, Young ho

• W. HUFNAGEL 'ALUMINIUM-SCHLUSSEL' 1983,
ALUMINIUM VERLAG, DUSSELDORF, DE * page



EP 0 635 579 B1

Description

The present invention relates to a horseshoe for race horses, made of a magnesium rich aluminum alloy. The object of this invention is to provide a light horseshoe for race horses excellent in abrasion resistance, shock absorption, and in ductility.

The horseshoe should primarily be light with ductility so that its shape may be changed a little to correctly fit on the horsehoof. It should also have abrasion resistance to long and dry frictions with the surface of the track and reduce the shock that occurs at the time of slipping on the track surface.

Since the conventional horseshoes were heavy as having been made mainly of mild steel, and poor in shock absorption because of their insufficient ductility, shoes have recently been made of alloyed aluminium buried with elastic shock-absorbing materials such as rubber and plastics but found difficult to protect the hooves and knee joints of the horse because of defects from their complex and easily breakable structure.

Since a race horse runs at a speed of 60 Km/hr during a race undergoing a shock of 1 ton in a moment (0.017 second), the horseshoes must be excellent in abrasion resistance and shock absorption and ductile enough to change their shape a little so as to suit the diverse sizes and forms of the hooves at the time of fitting on the later.

To improve and solve the problems of the conventional mild steel or aluminium horseshoes, the present invention relates to a horseshoe made of a magnesium rich aluminium alloy comprising in weight:

Si; 0.05-0.10%, Fe: 0.05-0.10%, Cu: 0.10-0.20%, Mn: 0.10-0.20%, Mg: 3.00-5.00%, Cr: 0.05-0.15%, Zn: 0.05-0.10% and Al: 98.6-99.15%

This alloy is only about one-third of the weight of the known mild steel horseshoe and excellent in abrasion-resistance, shock absorption and ductility. It is a 5XXX series aluminium alloy, which is non-heat treatable, and does not require precipitation hardening with solution and aging treatments.

The features of the present invention are described below:

A horseshoe for a race horse should primarily be capable of resisting frictions with the track surface, absorbing the momentary shock of one ton occurring from the speed of 60 Km/Hr during a race, and re-elsing abrasion therefrom. In view of this, the horseshoe according to the present invention which is as light as one-third of the conventional mild steel shoe, protects the hooves and knee joints of the race horse, enhances the racing speed and can be securely and perfectly fitted on the hoof by taking advantage of its ductility to modify its shape a little.

As, the aluminum alloy used for manufacturing the horseshoe according to the present invention is an aluminum alloy of the 5XXX series, it does not require precipitation hardening under solution and aging treatments.



3 / 4

OrderPatent

EP 0 635 579 B1

Table

Component Sample	Si	Fe	Cu	Mn	Mg	Cr	Zn	Al	tensile strength (kg/mm ²)	ductility (%)
1 The invention	0.08	0.08	0.11	0.13	5.00	0.12	0.05	94.88	30	25
2 Al-Cu Series	0.67	0.14	3.9	0.78	0.48	0.01	0.48	93.58	38	17
3 Al-Cu Series	0.05	0.13	4.00	0.50	1.30	-	0.05	93.80	44	14
4 Al-Zn Series	0.06	0.12	1.46	0.2	3.14	0.32	6.02	88.86	58	10
5 Al-Mg Series	0.04	0.13	0.03		2.18	0.28	0.06	97.28	54	13
6 Al-Mg-Zn Series	0.03	0.09	1.19		2.48	0.26	1.98	94.02	18	36



2

The biggest demerit of the aluminium alloys of the 5XXX series is their excessive Mg content, which causes too much stress corrosion cracking due to re-crystallization annealing, so that, the internal stress is removed to cause an excessive ductility and contraction, which again results in a low hardness and strength. In order to reduce the extreme abrasion resulted therefrom, an appropriately safe strength has been given by adjusting the content of Mg to be 3.00-5.00 wt% and adding 0.01-0.10 wt% of Zn thereto so that the shape of the shoe may be modified a little at the time of tilting. Furthermore, to increase anti-corrosive effects of impure materials, Fe is minimized to be 0.05-0.1 wt% and Cu and Mn are reduced respectively to be 0.10-0.20 wt%.

Further, the table below shows the chemical components and the tensile strength and ductility values of an alloy used for manufacturing a horseshoe according to the present invention, which is of the non-precipitation hardening type, as well as of Al-Cu series alloys and Al-Zn series alloy which are of the precipitation hardening type, and Al-Mg and Al-Mg-Zn series alloys which are other alloys of the non-precipitation hardening type.

55

05

54

40

35



04-05-2004 10:09:27 error: file not found

FP 0 635 579 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Seoul (KR)
Nam, Tae un
Seoul (FR)

75 - pag 80 ** ALLOY 5082*
• J.E. HATCH 'ALUMINIUM' 1984, AMERICAN
SOCIETY FOR METALS, OHIO, US * page 351 -
page 359 ** page 352, paragraph 3 - paragraph 4 *

7	Al-Mg Series	0.08	0.23	0.01		1.45	0.17	0.01	54.09	15	33
---	--------------	------	------	------	--	------	------	------	-------	----	----

As shown in this table, the invention horseshoe alloy is inferior in tensile strength to the Al-Cu series alloys, Al-Zn series alloy and one of the Al-Mg series alloys but far superior to the other Al-Mg series alloy while its ductility is much greater than the other series alloys with excellent abrasion resistance so that it gives room for modifying its shape as to suit the form of the hoof during fitting.

Al-Cu series alloys of samples 2 and 3, Al-Zn series alloy of sample 4 and Al-Mg-Zn series alloys were kept for 20 minutes at 480°C and for 30 minutes at 500°C. Then, they were placed one hour for solution treatment at 500°C and underwent aging treatment for 20 hours at 160°C. The Al-Mg-Zn and Al-Mg series alloys of samples 6 and 7, respectively, after going through solution treatment for two hours at 350°C, underwent annealing heat treatment. However, sample 1 made of the invention horseshoe alloy immediately underwent the annealing heat treatment without going through solution treatment.

The horseshoe according to the present invention is capable of reducing the area of contact with the track surface by the sloped height of its internal and external sides, minimizing the shock of contacting the track surface by evenly distributing the force, and, thereby increasing the durability of the horseshoe.

As stated above, the alloy used for manufacturing horseshoes for race horses according to the present invention is greater in ductility and lighter in weight than the existing mild steel, Al-Zn series alloy or Al-Cu and Al-Mg series alloys of the precipitation hardening type. It is also excellent in abrasion resistance and shock absorption with high ductility. Therefore, the shoes are easily fitted on the hooves and the manufacturing process of same can be rationalized.

Example of Application

The desired aluminum alloy to be used for manufacturing a horseshoe for a race horse is obtained by dissolving and mixing the pure aluminum 99.39 wt % made by ordinary method under Bayer process with Si:0.08 wt%, Fe:0.08



35

40

45

50

55



EP 0 635 579 B1

wt%, Cu:0.15 wt%, Mn:0.13 wt%, Cr:0.12 wt% and Zn:0.05 wt% in an electric furnace.

Claims

1. A horseshoe made of a magnesium rich aluminum alloy comprising in weight :

- Si: 0.05 - 0.10 %;
- Fe: 0.05 - 0.10 %;
- Cu: 0.10 - 0.20 %;
- Mn: 0.10 - 0.20 %;
- Mg: 3.00 - 5.00 %;
- Cr: 0.05 - 0.15 %;
- Zn: 0.05 - 0.10 %, and
- Al: 96.6 - 99.15 %.

Patentansprüche

- 20 1. Hußeisen bestehend aus einer magnesiumsreichen Aluminium-Legierung umfassend:

- | | |
|---|------------------------------|
| - | Si: 0,05 - 0,10 Gew. % ; |
| - | Fe: 0,05 - 0,10 Gew. % ; |
| - | Cu: 0,10 - 0,20 Gew. % ; |
| - | Mn: 0,10 - 0,20 Gew. % ; |
| - | Mg: 3,00 - 5,00 Gew. % ; |
| - | Cr: 0,05 - 0,15 Gew. % ; |
| - | Zn: 0,05 - 0,10 Gew. % , und |
| - | Al: 96,6 - 94,15 Gew. % . |



4 / 4

OrderPatent

Revendications

35 1. Fer à cheval fait d'un alliage d'aluminium riche en magnésium comprenant en poids :

- Si : 0,05 - 0,10 % ;
- Fe : 0,05 - 0,10 % ;
- Cu : 0,10 - 0,20 % ;
- Mn : 0,10 - 0,20 % ;
- Mg : 3,00 - 5,00 % ;
- Cr : 0,05 - 0,15 % ;
- Zn : 0,05 - 0,10 % ; et
- Al : 96,6 - 94,15 %.

40

45

50

55